

STARK METAL SALES, INC.

GAGE WEIGHT & THICKNESS

MSG No.	Hot Rolled, HR P&O, Cold Rolled					Galvanized				
	Thick. Equiv.	Tolerance HR, HRPO		Range CR		Lbs. per Sq. Ft.	Thick. Equiv.	Tolerance Range		Lbs. per Sq. Ft.
4	0.224	0.217	0.232			9.375				
5	0.209	0.202	0.218			8.750				
6	0.194	0.186	0.203			8.125				
7	0.179	0.187	0.171	0.187	0.171	7.500				
8	0.164	0.172	0.156	0.172	0.156	6.875	0.168	0.177	0.159	7.031
9	0.149	0.157	0.141	0.157	0.141	6.250	0.153	0.162	0.144	6.406
10	0.134	0.142	0.126	0.140	0.128	5.625	0.138	0.147	0.129	5.781
11	0.120	0.128	0.112	0.126	0.114	5.000	0.123	0.132	0.114	5.156
12	0.105	0.113	0.097	0.111	0.099	4.375	0.108	0.117	0.099	4.531
13	0.090	0.097	0.083	0.095	0.085	3.750	0.093	0.101	0.085	3.906
14	0.075	0.082	0.068	0.080	0.070	3.125	0.079	0.087	0.071	3.281
15	0.067	0.074	0.060	0.075	0.062	2.812	0.710	0.077	0.065	2.969
16	0.060	0.067	0.053	0.065	0.055	2.500	0.064	0.070	0.058	2.656
17	0.054	0.060	0.048	0.058	0.050	2.250	0.058	0.063	0.053	2.406
18	0.048	0.054	0.042	0.052	0.044	2.000	0.052	0.057	0.047	2.156
19	0.042			0.046	0.036	1.750	0.046	0.051	0.041	1.906
20	0.036			0.039	0.033	1.500	0.040	0.044	0.036	1.656
21	0.033			0.036	0.030	1.375	0.037	0.041	0.033	1.531
22	0.030			0.033	0.027	1.250	0.034	0.038	0.030	1.406
23	0.027			0.030	0.240	1.125	0.031	0.035	0.027	1.281
24	0.024			0.027	0.021	1.000	0.028	0.032	0.024	1.156
25	0.021			0.024	0.018	0.875	0.025	0.029	0.021	1.031
26	0.018			0.020	0.016	0.750	0.022	0.025	0.019	0.906
27	0.016			0.018	0.014	0.688	0.020	0.023	0.017	0.844
28	0.015			0.017	0.013	0.625	0.019	0.022	0.016	0.781
29	0.014			0.016	0.012	0.562	0.017	0.020	0.014	0.719
30	0.012			0.014	0.010	0.500	0.016	0.019	0.013	0.656

STARK METAL SALES, INC.

PHONE: (330) 823-7383 FAX: (330) 823-5949